



# Polyolefins







---

## Jacketing Cable Compounds



## Jacketing Cable Compounds

### Description

-  Excellent Stress Crack resistance (ESCR)
-  Excellent Processability
-  Perfect Long-Term Outdoor Weathering Resistance
-  Good Physical Properties
-  Excellent Low Temperature Properties
-  Excellent Smooth & Shiny Surface Finish

### Application

-  For (Linear) Low, Medium and High Density Black Jacket Cable Applications

<i>Class</i>	<i>Grade</i>	<i>Density (g/cm<sup>3</sup>)</i>	<i>Melting flow index (g/10min)</i>	<i>Material</i>
<i>PE Thermoplast</i>	<b>CLBB-850BK</b>	0.933	0.25	LDPE
	<b>CLBA-8450BK</b>	0.934	0.8	LLDPE
	<b>CMBA-8240BK</b>	0.949	0.23	MDPE
	<b>CHBA-8241BK</b>	0.955	0.23	HDPE
	<b>HEC-W-320-K</b>	0.985	0.5	HDPE
	<b>HEC-SC-600</b>	1.050	0.21	HDPE Semicond
<i>PE Thermoplast HFFR</i>	<b>HEC-SH-320NFR-SC</b>	1.550	5.0	HFFR PE
<i>PE Thermofix</i>	<b>HEC-SH-300IX-CD</b>	1.410	5.0	Silane XLPE
<i>PE</i>	<b>HEC-SC-9000NFR</b>	1.300	1.5	HFFR PE
<i>PVC</i>	<b>HEC-PVC-ST-2(88)</b>	1.470		PVC